



TECHNICAL DATA SHEET

DECOmid B1S0HZL

PROPERTIES		STANDARD	UNIT	TYPICAL VALUES
------------	--	----------	------	----------------

PHYSICAL & THERMAL

Density		ISO 1183	g/cm ³	1,06
Melting Point		DSC	°C	222
Mold Shrinkage (average)		ISO 294-4	%	1,8 - 2,2
Moisture Absorption (water immersion)	23oC - 24h	ISO 62	%	1,2
Melt Flow Index		ISO 1133	g/10min	-
Vicat Softening Temperature B	9,8 N	ISO 306	°C	180
Heat Deflection Temperature0,45 MPa		ISO 75-2	°C	140
Heat Deflection Temperature1,81 MPa		ISO 75-2	°C	50
Heat Resistance / Ball test		IEC 335-1 IEC 60695-10-2	°C	> 165
Continuous Use Temperature (without load)		IEC 60216	°C	75

MECHANICAL

Tensile Strength at Yield		ISO 527	MPa	50
Tensile Strength at Break		ISO 527	MPa	-
Tensile Modulus		ISO 527	MPa	1700
Tensile Strain at Yield		ISO 527	%	8
Tensile Strain at Break		ISO 527	%	>100
Izod - Notched Impact Strength		ISO 180/A	KJ/m ²	65
Izod - Unnotched Impact Strength		ISO 180/U	KJ/m ²	NB

ELECTRICAL & FLAME RETARDANCY

Comparative Tracking Index (CTI)		IEC 60112	V	600
Flammability	3,2 / 1,6 / 0,8 mm	UL 94	-	HB
Glow Wire Ignition Temperature	GWIT – 2 mm	IEC 60695-2-12	°C	-
Glow Wire Flammability Index	GWFI - 2 mm	IEC 60695-2-12	°C	650

Molding conditions (suggested)

Drying Temperature > 3 h / 90 – 100 °C	Molding temperature 255 – 275 °C	Mold temperature 70 - 90 °C
--	----------------------------------	-----------------------------

The information contained herein are supplied in good faith and given purely as an indication. Properties should be carefully evaluated for all projects requirements. Unless otherwise posted this product is not suitable for food and/or medical application and use. They shall not be considered in any way as a formal commitment or warranty on our part especially in case of improper use of our products from third parties.

16.03.2018